

MECHANICAL, THERMAL, MORPHOLOGICAL AND RHEOLOGICAL
PROPERTIES OF POLY(LACTIC ACID)/ NATURAL RUBBER/ CARBON
NANOTUBE NANOCOMPOSITES

NOR NISA BALQIS BINTI MOHAMMAD

UNIVERSITI TEKNOLOGI MALAYSIA

MECHANICAL, THERMAL, MORPHOLOGICAL AND RHEOLOGICAL
PROPERTIES OF POLY(LACTIC ACID)/ NATURAL RUBBER/ CARBON
NANOTUBE NANOCOMPOSITES

NOR NISA BALQIS BINTI MOHAMMAD

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Doctor of Philosophy in (Polymer Engineering)

School of Chemical and Energy Engineering
Faculty of Engineering
Universiti Teknologi Malaysia

SEPTEMBER 2020

ACKNOWLEDGEMENT

In the name of Allah, of going through this academic journey were indeed very memorable experiences. All praises to Allah the Almighty for giving me the strengths, guidance and patience in completing this thesis. With His blessing, this thesis is finally accomplished.

First of all, I would like to express my genuine gratitude to my supervisors Dr Agus bin Arsad, P.M. Dr. Abdul Razak bin Rahmat and Dr Mohamad Shukor bin Talib for their on-going support and encouragement during period of my studies. Also, deep appreciation to Dr Hyoung Jin Choi from Inha University, Korea, who provided me an opportunity to join his research team and gave me access to the laboratory and research facilities. Special thanks to all staff and technicians of Polymer Engineering Laboratory for giving help and making the lab an enjoyable place to work. Without their precious support it would not be possible to conduct this research.

Last but not least, I wish to express my sincere thanks to my lovely parents and family for all the sacrifices which they have done on my behalf. Also, thanks to the person who cares and supported me spiritually in writing, and incited to strive towards my goal. At the end, special gratitude to my beloved husband, Muhammad Noor Akmal bin Mokhtar, who was always be my backbone in the moments of uncertainties and difficulties. Your prayer for me was what sustained me thus far.

ABSTRACT

Inherent brittleness in poly(lactic acid) (PLA) largely limit its wide applications as common biodegradable plastic materials. Thus, PLA toughening through melt blending was prepared by incorporating different ratio of natural rubber (NR) (0% to 20%) as toughening agents to investigate the mechanical, thermal, morphological and rheological properties of the PLA/NR blends. This approach used 9 wt.% of two different types of compatibilizers natural rubber-grafted-maleic anhydride (NR-g-MA) and polylactic acid-grafted-maleic anhydride (PLA-g-MA) in the system to enhance compatibility between PLA and NR. Then, to improve stiffness and strength of the blends, addition 1-8 phr of nanofiller pristine carbon nanotube (CNT) was added into the system to prepare PLA/NR nanocomposites. The result of mechanical properties the blends showed good performance significantly for impact strength. Additionally, thermal properties of the blends and nanocomposites were investigated by using thermogravimetric analysis and differential scanning calorimetry. The results showed an increase in glass transition temperature and thermal stability by addition of CNT. Scanning electron microscopy and nanoscanning electron microscopy were conducted and revealed good dispersion of CNT particles in the PLA matrix at higher amount (8phr). Moreover, X-ray diffraction analysis was carried out for microstructure properties determination for nanocomposites and showed good interactions between PLA and CNTs. Finally, melt flow index and rotational rheometer were used to characterize the rheological properties of the blends and nanocomposites. Increasing for storage modulus and loss modulus were observed in the system with addition of CNT. Experimental data obtained from rheological analysis for all these three systems were used for mathematical model approaches using Power Law and Carreau - Yasuda models to study the rheological behaviour of blends. Power Law model has the best fit and more suitable for shear-thinning behaviour because of low range shear rate system for this particular study compared to Carreau-Yasuda. As a conclusion, additional of compatibilizer and CNT led blend properties to increase significantly in impact strength and thermal stability.

ABSTRAK

Sifat rapuh poli(asid laktik) (PLA) sebahagian besar membataskan keluasan penggunaannya sebagai bahan plastik terbiodegradasi. Oleh itu, pengukuhan PLA melalui pengandungan leburan disediakan dengan mencampurkan nisbah getah asli yang berbeza (0% hingga 20%) sebagai agen pengukuh untuk mengkaji sifat-sifat mekanikal, haba, morfologi dan reologi adunan PLA/NR tersebut. Penggunaan 9% berat dua jenis penserasi yang berbeza (getah asli-cantuman-maleik anhidrida (NR-g-MA) dan asid poli(asid laktik)-cantuman-maleik anhidrida (PLA-g-MA)) di dalam sistem adalah untuk meningkatkan keserasian antara PLA dan NR. Kemudian, bagi meningkatkan kekakuan dan kekuatan adunan, sebanyak 1-8 phr tiub karbon nano asli (CNT) ditambahkan ke dalam sistem untuk menghasilkan PLA/NR komposit nano. Hasil menunjukkan peningkatan ketara untuk sifat-sifat mekanik terutamanya kekuatan hentaman. Tambahan lagi, sifat-sifat terma campuran polimer dan komposit nano dikaji dengan menggunakan analisa termogravimetrik dan kalorimetri imbasan keberbezaan. Keputusan menunjukkan peningkatan suhu peralihan kaca dan kestabilan haba dengan penambahan CNT. Mikroskop elektron imbasan dan mikroskop elektron imbasan nano dijalankan dan mendedahkan serakan zarah CNT adalah lebih baik dalam matrik PLA pada kandungan yang lebih tinggi (8 phr). Selain itu, analisis pembelauan sinar-X telah dijalankan untuk menentukan sifat struktur mikro untuk komposit nano dan menunjukkan ikatan antara PLA and CNT. Akhir sekali, indeks aliran leburan dan reometer putaran digunakan untuk mencirikan sifat reologi campuran dan komposit nano. Peningkatan modulus penyimpanan dan modulus hilang dengan penambahan jumlah CNT. Data yang diperolehi daripada analisis reologi untuk dicerapkan dalam ketiga-tiga sistem ini digunakan dalam kajian model matematik menggunakan model hukum kuasa dan Carreau - Yasuda bagi mengkaji kelakuan reologi campuran tersebut. Model hukum kuasa lebih sesuai terhadap kelakuan penipisan ricih kerana sistem kadar ricih yang rendah digunakan dalam kajian ini berbanding model Carreau-Yasuda. Kesimpulannya, penambahan bahan penserasi dan CNT telah menyebabkan peningkatan sifat campuran terutama kekuatan hentaman dan kestabilan haba.

TABLE OF CONTENTS

| | TITLE | PAGE |
|------------------|--|--------------|
| | DECLARATION | iii |
| | DEDICATION | iv |
| | ACKNOWLEDGEMENT | v |
| | ABSTRACT | vi |
| | ABSTRAK | vii |
| | TABLE OF CONTENTS | viii |
| | LIST OF TABLES | xii |
| | LIST OF FIGURES | xiii |
| | LIST OF ABBREVIATIONS | xvi |
| | LIST OF SYMBOLS | xviii |
| CHAPTER 1 | INTRODUCTION | 1 |
| 1.1 | Research Background | 1 |
| 1.2 | Problem Statement | 4 |
| 1.3 | Research Objectives | 6 |
| 1.4 | Scopes of Research | 6 |
| CHAPTER 2 | | 9 |
| 2.1 | Biodegradable Polymer | 9 |
| 2.1.1 | Poly(lactic acid) (PLA) | 10 |
| 2.1.2 | Synthesis of PLA | 11 |
| 2.1.3 | Properties of PLA | 14 |
| 2.1.4 | PLA Blends | 15 |
| 2.2 | Natural Rubber | 17 |
| 2.2.1 | Rubber-Toughened Polylactic Acid | 18 |
| 2.2.2 | Natural Rubber-Toughened Polylactic Acid | 19 |
| 2.3 | Compatibilizer | 23 |
| 2.3.1 | Maleic Anhydride | 24 |

| | | |
|------------------|--|-----------|
| 2.3.2 | Maleated Natural Rubber (NR-g-MA) | 25 |
| 2.3.3 | Maleated Polylactic Acid (PLA-g-MA) | 27 |
| 2.4 | Nanocomposite | 29 |
| 2.5 | Nanofiller | 30 |
| 2.5.1 | Carbon Nanotube (CNT) | 31 |
| 2.5.2 | PLA Nanocomposite | 34 |
| 2.5.3 | PLA/CNT Nanocomposite | 36 |
| 2.6 | Rheological Study | 38 |
| 2.6.1 | Viscosity | 38 |
| 2.6.2 | Non Newtonian Fluid | 42 |
| 2.7 | Rheological Mathematical Models | 44 |
| 2.7.1 | Power Law model | 45 |
| 2.7.2 | Carreau - Yasuda Model | 47 |
| CHAPTER 3 | RESEARCH METHODOLOGY | 51 |
| 3.1 | Materials | 51 |
| 3.2 | Sample Preparation and Characterization Work Flow | 52 |
| 3.3 | Synthesis of Compatibilizers (Maleated Natural Rubber (NR-g-MA) and Maleated PLA (PLA-g-MA)) | 52 |
| 3.3.1 | Characterization for compatibilizer | 53 |
| 3.4 | Blend Polymer Preparations | 53 |
| 3.4.1 | PLA/NR and PLA/NR/compatibilizer | 53 |
| 3.4.2 | PLA/NR/compatibilizer/CNT Nanocomposite | 55 |
| 3.5 | Characterizations | 56 |
| 3.5.1 | Tensile Test | 56 |
| 3.5.2 | Flexural Test | 57 |
| 3.5.3 | Impact Test | 57 |
| 3.5.4 | Differential Scanning Calometry (DSC) | 57 |
| 3.5.5 | Thermalgravimetric Analysis (TGA) | 58 |
| 3.5.6 | Scanning Electron Microscopy (SEM) | 58 |
| 3.5.7 | NanoScanning Electron Microscope (NanoSEM) | 59 |
| 3.5.8 | X-ray Diffraction (XRD) Analysis | 59 |

| | | |
|------------------|---|-----------|
| 3.5.9 | Melt Flow Index (MFI) Analysis | 60 |
| 3.5.10 | Rotational Rheometer Test | 60 |
| 3.6 | Rheological Mathematical Models | 60 |
| CHAPTER 4 | RESULTS AND DISCUSSIONS | 61 |
| 4.1 | Characterizations of PLA/NR and PLA/NR/Compatibilizers Blends | 61 |
| 4.1.1 | Melt flow Index (MFI) | 61 |
| 4.1.2 | Fourier-Transform Infrared Spectroscopy (FTIR) Analysis | 62 |
| 4.1.3 | Mechanical Properties | 64 |
| 4.1.3.1 | Tensile Properties | 64 |
| 4.1.3.2 | Flexural Test | 67 |
| 4.1.4 | Thermal Analysis | 72 |
| 4.1.4.1 | Differential Scanning Calorimetry (DSC) | 72 |
| 4.1.4.2 | Thermal Gravimetric Analysis (TGA) | 75 |
| 4.1.5 | Scanning Electron Microscopy (SEM) | 80 |
| 4.1.6 | Rotational Rheometer Analysis | 85 |
| 4.2 | Characterizations of PLA/NR/Compatibilizer/CNT Nanocomposites | 92 |
| 4.2.1 | Mechanical Properties | 92 |
| 4.2.1.1 | Tensile Properties | 92 |
| 4.2.1.2 | Flexural Test | 96 |
| 4.2.1.3 | Impact test | 97 |
| 4.2.2 | Thermal Analysis | 99 |
| 4.2.2.1 | Differential Scanning Calorimetry (DSC) | 99 |
| 4.2.2.2 | Thermal Gravimetric Analysis (TGA) | 104 |
| 4.2.3 | Nano Scanning Electron Microscopy (NanoSEM) | 108 |
| 4.2.4 | X-ray Diffraction (XRD) Analysis | 113 |
| 4.2.5 | Rotational Rheometer Analysis | 115 |

| | | |
|-------------------|--|------------|
| 4.3 | Rheological Mathematical Models Analysis | 123 |
| 4.3.1 | Power Law Model | 123 |
| 4.3.2 | Carreau – Yasuda Model | 128 |
| CHAPTER 5 | CONCLUSION AND RECOMMENDATIONS | 133 |
| 5.1 | Conclusion | 133 |
| 5.2 | Recommendations | 137 |
| REFERENCES | | 139 |

LIST OF TABLES

| TABLE NO. | TITLE | PAGE |
|------------------|--|-------------|
| Table 3.1 | Specification of PLA from supplier | 51 |
| Table 3.2 | Formulation of PLA/NR | 54 |
| Table 3.3 | Formulation of PLA/NR/compatibilizers | 54 |
| Table 3.4 | Formulation of PLA/NR/compatibilizer/CNT | 55 |
| Table 4.1 | T _g , T _m , ΔH _m and X _c value from 1 st heating of pure PLA, PLA/NR blends and both compatibilized PLA/NR blends. | 72 |
| Table 4.2 | T _g , T _m , ΔH _m and X _c value from 2 nd heating of pure PLA, PLA/NR blends and both compatibilized PLA/NR blends. | 73 |
| Table 4.3 | Thermogravimetric data for pure PLA, PLA/NR blends and both compatibilized PLA/NR blends | 79 |
| Table 4.4 | T _g , T _m , ΔH _m and X _c value from 1 st heating of pure PLA, PLA/NR/ PLA-g-MA/CNT and PLA/NR/NR-g-MA/CNT nanocomposites. | 103 |
| Table 4.5 | T _g , T _m , ΔH _m and X _c value from 2 nd heating of pure PLA, PLA/NR/ PLA-g-MA/CNT and PLA/NR/NR-g-MA/CNT nanocomposites. | 103 |
| Table 4.6 | TGA data (T ₅ , T ₅₀ , T _d , and residual mass) of both PLA/NR/PLA-g-MA/CNT and PLA/NR/NR-g-MA/CNT nanocomposites. | 108 |
| Table 4.7 | Power law data of pure PLA, PLA/NR/Compatibilizers blends with and without CNT fillers obtained from rheological testing previously. | 125 |
| Table 4.8 | Parameters used in the Carreau – Yasuda model for pure PLA and both PLA/NR/PLA-g-MA/CNT and PLA/NR/MA-g-MA/CNT nanocomposites. | 131 |

LIST OF FIGURES

| FIGURE NO. | TITLE | PAGE |
|-------------|---|------|
| Figure 2.1 | Chemical structure of L and D-lactic acid (m.p. is melting point) (Auras <i>et al.</i> , 2004). | 12 |
| Figure 2.2 | Synthesis methods for obtaining high molecular weight PLA (Auras <i>et al.</i> , 2004) | 13 |
| Figure 2.3 | Molecular structure of Natural Rubber | 17 |
| Figure 2.4 | Impact strength of PLA, PLA/NR (90/10) and PLA/NR/NR-g-GMA at various % grafting of NR-g-GMA (Juntuek <i>et al.</i> , 2012). | 20 |
| Figure 2.5 | SEM micrographs of freeze-fractured surfaces of (a) pure PLA, (b ₁) 5 wt% and (b ₂) 20 wt% NR/PLA blend, (c ₁) 5 wt% and (c ₂) 20 wt% NR-g-PBA/PLA blend (Zhang <i>et al.</i> , 2011). | 21 |
| Figure 2.6 | The possible reaction of natural rubber and maleic anhydride (Nakason <i>et al.</i> , 2004). | 26 |
| Figure 2.7 | Mechanism of maleated PLA (Carlson <i>et al.</i> , 1999) | 27 |
| Figure 2.8 | Type of carbon nanotube (a) SWNT, single-walled carbon nanotube; (b) DWCNT, double-walled carbon nanotube; (c) MWNT, multi-walled carbon nanotube; (d) carbon nanohorn; (e) carbon nanobud; (f) carbon nanotorus. (Beg <i>et al.</i> , 2010). | 34 |
| Figure 2.9 | Flow between two parallel plates. | 39 |
| Figure 2.10 | Various type of common flow behaviour. | 40 |
| Figure 2.11 | Relationship of modulus. | 41 |
| Figure 3.1 | Sample Preparation and characterization work flow of PLA/NR/CNT | 52 |
| Figure 4.1 | Melt flow index of PLA/NR blends. | 62 |
| Figure 4.2 | FTIR spectra of NR and PLA/NR/NR-g-MA blends | 63 |
| Figure 4.3 | FTIR spectra of PLA and PLA/NR/PLA-g-MA blends. | 64 |
| Figure 4.4 | Tensile properties (a) Tensile strength, (b) Young's Modulus and (c) elongation at break of pure PLA (0% NR), PLA/NR, PLA/NR/PLA-g-MA and PLA/NR/NR-g-MA blends. | 67 |

| | | |
|-------------|--|-----|
| Figure 4.5 | Flexural properties (a) Flexural strength and (b) Flexural Modulus of pure PLA, PLA/NR, PLA/NR/PLA-g-MA and PLA/NR/NR-g-MA blends. | 69 |
| Figure 4.6 | Impact properties of pure PLA, PLA/NR, PLA/NR/PLA-g-MA and PLA/NR/NR-g-MA blends. | 71 |
| Figure 4.7 | TGA curves of pure PLA and (a) PLA/NR blends, (b) PLA/NR/PLA-g-MA blends (c) PLA/NR/NR-g-MA blends. | 77 |
| Figure 4.8 | SEM micrographs of PLA/NR blend: (a) pure PLA, (b) PLA95/NR5, (c) PLA90/NR10, (d) PLA85/NR15 and (e) PLA80/NR20 | 81 |
| Figure 4.9 | SEM micrographs of PLA/NR/Compatibilizers blend: (a) PLA85/NR15/PLA-g-MA and (b) PLA85/NR15/NR-g-MA. | 83 |
| Figure 4.10 | Effect of compatibilizer addition on viscosity of (a) PLA/NR, (b) PLA/NR/PLA-g-MA and (c) PLA/NR/NR-g-MA blends. | 86 |
| Figure 4.11 | Effect of compatibilizer addition on storage modulus, (G') of (a) PLA/NR, (b) PLA/NR/PLA-g-MA and (c) PLA/NR/NR-g-MA blends. | 89 |
| Figure 4.12 | Effect of compatibilizer addition on loss modulus, (G'') of (a) PLA/NR, (b) PLA/NR/PLA-g-MA and (c) PLA/NR/NR-g-MA blends. | 90 |
| Figure 4.13 | Tensile properties (a) Tensile Strength, (b) Young's Modulus and (c) elongation at break of PLA/NR/PLA-g-MA/CNT and PLA/NR/NR-g-MA/CNT nanocomposites. | 94 |
| Figure 4.14 | Flexural properties (a) Flexural Strength and (b) Flexural Modulus of PLA/NR/PLA-g-MA/CNT and PLA/NR/NR-g-MA/CNT nanocomposites. | 97 |
| Figure 4.15 | Impact properties of PLA/NR/PLA-g-MA/CNT and PLA/NR/NR-g-MA/CNT nanocomposites. | 98 |
| Figure 4.16 | DSC thermograms (a) PLA/NR/PLA-g-MA/CNT and (b) PLA/NR/NR-g-MA/CNT nanocomposites at various contents of CNT. | 100 |
| Figure 4.17 | TGA curves of (a) PLA/NR/PLA-g-MA and (b) PLA/NR/NR-g-MA nanocomposites at various contents of CNT. | 105 |
| Figure 4.18 | DTG curves of (a) PLA/NR/PLA-g-MA and (b) PLA/NR/NR-g-MA nanocomposites at various contents of CNT. | 106 |

| | | |
|-------------|---|-----|
| Figure 4.19 | NanoSEM micrographs of PLA/NR/Compatibilizers/CNT nanocomposites: (a) PLA85/NR15/PLA-g-MA, (b) PLA85/NR15/PLA-g-MA/1CNT, (c) PLA85/NR15/PLA-g-MA/4CNT and (d) PLA85/NR15/PLA-g-MA/8CNT. | 109 |
| Figure 4.20 | NanoSEM micrographs of PLA/NR/Compatibilizers/CNT nanocomposites: (a) PLA85/NR15/NR-g-MA (b) PLA85/NR15/NR-g-MA/1CNT, (c) PLA85/NR15/NR-g-MA/4CNT and (d) PLA85/NR15/NR-g-MA/8CNT. | 110 |
| Figure 4.21 | X-ray intensity distribution for pure PLA, PLA/NR/PLA-g-MA/8CNT and PLA/NR/NR-g-MA/8CNT. | 113 |
| Figure 4.22 | X-ray intensity distribution of a pristine CNT. | 114 |
| Figure 4.23 | Effect of CNT content on viscosity of (a) PLA/NR/PLA-g-MA/CNT and (b) PLA/NR/NR-g-MA/CNT nanocomposites. | 116 |
| Figure 4.24 | Effect of CNT content on storage modulus, (G') of (a) PLA/NR/PLA-g-MA/CNT and (b) PLA/NR/NR-g-MA/CNT nanocomposites. | 118 |
| Figure 4.25 | Effect of CNT content on loss modulus, (G'') of (a) PLA/NR/PLA-g-MA/CNT and (b) PLA/NR/NR-g-MA/CNT nanocomposites. | 119 |
| Figure 4.26 | Plots of $\tan \delta$ vs. frequency at variation amount of pristine CNT for (a) PLA/NR/PLA-g-MA/CNT and (b) PLA/NR/NR-g-MA/CNT nanocomposites. | 121 |
| Figure 4.27 | (a) Power Law index (n) and (b) constant k of PLA/NR/PLA-g-MA/CNT and PLA/NR/NR-g-MA/CNT nanocomposites with various amounts of CNT filler. | 126 |
| Figure 4.28 | Comparison graph between experimental data and Power law model of (a) PLA/NR/PLA-g-MA/CNT and (b) PLA/NR/NR-g-MA/CNT nanocomposites with various amounts of CNT filler. | 127 |

LIST OF ABBREVIATIONS

| | | |
|-------------|---|---|
| CNT | - | Carbon Nanotube |
| CCVD | - | Catalytic Chemical Vapour Deposition |
| CVD | - | Condensation–Vaporization Densation |
| DWCNT | - | Double-walled Carbon Nanotube |
| ENR | - | Epoxidized Natural Rubber |
| EPR | - | Ethylene Propylene Rubber |
| EPDM | - | Ethylene propylene diene monomer |
| MA | - | Maleic Anhydride |
| MAH-g-EPM | - | Maleic Anhydride grafted Ethylene Propylene Rubber |
| MA-g-NR | - | Maleic Anhydride grafted Natural Rubber |
| MA-g-PLA | - | Maleic Anhydride grafted Polylactic Acid |
| MAH-g-PP | - | Maleic Anhydride grafted Polypropylene |
| MM | - | Molecular Modelling |
| MMT | - | Montmorillonite |
| MW | - | Molecular Weight |
| MWCNT | - | Multiwalled Carbon Nanotube |
| MWCNT-g-PLA | - | Multiwalled carbon nanotube grafted Polylactic Acid |
| NBR | - | Acrylonitrile–butadiene rubber |
| NR | - | Natural Rubber |
| NR-g-GMA | - | Glycidyl methacrylate-grafted natural rubber |
| NR-g-PBA | - | Natural Rubber grafted Poly(butyl acrylate) |
| NR-g-PMMA | - | Poly(methyl methacrylate) grafted natural rubber |
| OMLS | - | Organically modified layered silicate |
| PCV | - | Polyvinyl Chloride |
| Phr | - | Parts per hundred |
| PE | - | Polyethylene |
| PET | - | Polyethylene Terephthalate |
| PLA | - | Polylactic acid |

| | | |
|----------------|---|--|
| PP | - | Polypropylene |
| PS | - | Polystyrene |
| ROP | - | Ring-opening polymerization |
| SWCNT | - | Single-walled Carbon Nanotubes |
| T _c | - | Crystalline Temperature |
| T _g | - | Glass Transition Temperature |
| T _m | - | Melting Temperature |
| ASTM | - | American Society for Testing and Materials |
| DSC | - | Differential Scanning Calorimetry |
| MFI | - | Melt Flow Index |
| SEM | - | Scanning Electron Microscopy |
| TEM | - | Transmission Electron Microscopy |
| TGA | - | Thermalgravimetric Analysis |
| XRD | - | X-ray Diffraction Analysis |

LIST OF SYMBOLS

| | | |
|--------------------|---|---------------------------------|
| $^{\circ}\text{C}$ | - | Degree Celcius |
| J/m | - | Joule per Meter |
| g/10 min | - | Gram per 10 Minutes |
| g/cm^3 | - | Gram per Centimeter Cubic |
| kg | - | Kilogram |
| $\text{wt}\%$ | - | Weight Percent |
| J | - | Joule |
| $\%$ | - | Percentage |
| MPa | - | Mega Pascal |
| kg/cm^2 | - | Kilogram per Centimeter Square |
| rpm | - | rotation per minute |
| χ | - | Flory–Huggins interaction |
| η^* | - | Complex Viscosity |
| η | - | Viscosity |
| η^{∞} | - | Infinite shear viscosity |
| γ | - | Frequency |
| ω | - | Shear rate or angular frequency |
| λ | - | Time constant |

CHAPTER 1

INTRODUCTION

1.1 Research Background

For the past decades, various petrochemical-based polymers were widely contributed in economical, processing and technological aspect. But, after rapid development in these polymers, constant environmental pollution occurred caused by undegradable polymers wastes. Recycling present polymer wastes is a direct and popular approach toward solving the environmental pollution problem. Indeed, developing and using biodegradable polymers is considered as the most utter method for resolving this situation. Due to the public concern regarding these situations, the increasing inclination of manufacturing companies to develop more sustainable products, limited fossil fuel resources, and climate change are significant reasons for governments and companies to find substitutes to crude oil-based products. Green-based polymers present enormous potential to reduce the dependence on fossil fuels and the related environmental impacts. It is a barely new technology but it has been growing concern and a quite lot of them have been industrialized.

Among all these polymers, polylactide (PLA) is one of the biodegradable polymers that can be used as promising alternative to the petroleum based commodity materials, because they can be derived from renewable resources, such as corn, potato, and other agricultural products (Kaci *et al.*, 2012). Polylactic acid (PLA) is a thermoplastic polymer derived from biomass and it is aliphatic polyester producible from renewable resources such as starch and sugar. Apparently, because of its renewability, biodegradability, and greenhouse gas neutrality, it has been emerging as an alternative to conventional petroleum-based polymeric materials. Even though biodegradable polymers have been developed a remarkable speed and the successful situation in this field is quite inspiring, they are far from becoming substitutes for traditional undegradable polymers.

According to Zhang *et al.*, (2011), due to its resource renewability and environmental degradability, PLA holds excellent potential as an alternative to traditional petroleum-based materials. However, there are limitation in their applications in the inherent brittleness, low-melt viscosity, and low-heat distortion temperature. Brittleness, low impact resistance, and high cost, especially, the sensitivity to the temperature of PLA, limit the use of PLA in the engineering field (Zhang *et al.*, 2012). These limits the applications of PLA that driving to replace the conventional thermoplastics (Jaratrotkamjorn *et al.*, 2012).

According to these circumstances, modifications for PLA were approached to improve the properties of PLA. Some techniques such as processing manipulation, copolymerization and blending have been tried to modify the mechanical brittleness of PLA (Zhang *et al.*, 2012). Supported by Zhang *et al.*, (2012) stated that; except for chemical modification of PLA, physical blending was suitable to use to improve the properties of PLA. As stated by Liu and Zhang (2011), melt blending of polymers is a much more economical and convenient methodology than synthesizing a new polymers to achieve the properties unattainable with existing polymers. It is common practice where modification of PLA is to blend with flexible polymers. However, the improvement of mechanical properties of PLA is still necessary to obtain such elastomer or rubber with optimum performance (Juntuek *et al.*, 2012).

For this particular study, natural rubber (NR) is chosen because is an ideal candidate as toughening agent for PLA. NR is widely used in various applications particularly for tires because of its excellent elastic properties over other synthetic counterparts (Saelao and Phinyocheep, 2005). Jaratrotkamjorn *et al.*, (2012) reported natural rubber is an eco-friendly rubber and derived from a renewable resource. NR should be a good toughening agent due to its high molecular weight and very low glass transition temperature ($\sim -70^{\circ}\text{C}$). This is the reason NR is an interesting candidate as impact modifier for PLA. It has excellent properties with high strength, high resilience, and high elongation at break (Mark, 1970). Even though, impact toughness improvement of PLA is greatly achieved; some drawbacks in strength and stiffness possibly could be a resistance towards polymer blend to obtain optimized properties.

In producing an advanced biodegradable composite in this research, carbon nanotube (CNT) is chosen to promote as nanofiller further enhance in the mechanical, electrical and thermal conductivity performance of PLA as nanofiller. Based on previous studies on CNT, it was considered to be an ideal filler high performance polymer composite. As expected with high aspect ratio and high modulus, experimentally introducing CNTs into a polymer improves remarkably the mechanical properties, crystallization and electrical conductivity of the matrix (Wu *et al.*, 2008). Moreover, as nanofillers; CNT can also be more successful than others attending to its reduced diameter and its high surface-volume ratio (Pinto *et al.*, 2015). Therefore, high expectation to further improve PLA properties can be achieved by using CNT as nanofillers in this research.

Unfortunately, the non-polarity of NR makes PLA/NR blends is usually immiscible. Generally, chemically different polymers are immiscible and their blending leads to weak interfacial adhesion and thus poor mechanical integrity (Sadiku-Agboola *et al.*, 2011). In the case of PLA/NR blends, the difference in the polarity and molecular weight of PLA and NR may result in the poor compatibility between PLA and NR. And lead to poor impact strength (Juntuek *et al.*, 2012). Regarding to this problem, it is difficult to achieve an optimum properties because of literally the mechanical properties are strongly dependent on the interfacial characteristic between two components and stabilization of desired morphology or material structure.

This problem can be solved through grafting and improved its rheological, adhesive, thermal and curing performance. One of the classical approaches to improve the adhesion between the phases (reduction in the interfacial tension) is the use of a third component, a compatibilizer by graft copolymerization, which is usually a macromolecule designed to manipulate the interfacial properties (Elias *et al.*, 2007).

Since graft copolymers consisting of chemically identical segments of some polymeric constituents in the blends, they provide the higher phase compatibility resulting in the improved mechanical properties of the obtained finished product (Sookprasert *et al.*, 2017). Therefore, improvement of interfacial interaction between PLA and NR should be made by introducing maleic anhydride grafted NR or PLA in graft copolymerization as compatibilizer.

In this study, rheological mathematical models of non-Newtonian behaviour were required in order to understand the structure-properties relationship of polymer compounds. Despite its importance for industrial applications, the issue of how the rheology of a shear-thinning fluid affects the characteristics of two-phase stratified flow at different flow conditions is not yet completely understood. Only few works have been published on stratified flows in the presence of shear-thinning fluids (Picchi *et al.*, 2017). This may help us to clearly understand to behind of the physical properties of the polymer materials. As the result; in this project, Power Law and Carreau-Yasuda models were applied to describe the effect of shear – thinning behaviour of polymer melts and clearly understand the results from the experimental method in the rheological part. As described in Pinarbasi and Liakopoulus (2005), Carreau-Yasuda fits accurately many experimental viscosity curves over a wide range of shear rate.

1.2 Problem Statement

Limitation in PLA application has been recognized due to its brittleness and poor crystallisation. PLA toughness is one way to overcome this limitation, where natural rubber is chosen as impact modifier in this project. However, the difference in polarity between natural rubber and PLA may led to poor compatibility and poor mechanical properties especially impact strength.

According to the Hwang *et al.*, (2012), the formation of single and oligomeric grafts by grafting of Maleic anhydride onto polyolefins, and proposed that a bridge could be formed between grafted maleic Anhydride and polymer chains. It may lead to improve mechanical properties of polymer. Thus, reactive compatibilizer was used in this study to overcome the limitation in PLA and NR blend.

On the other hand, melt blending PLA with NR may greatly enhance impact toughness but the reductions in tensile strength and stiffness of the PLA materials still remains a challenge. Due to that, in this study CNT will be added as nanofiller or reinforcement agent in order to increase the strength and stiffness of material. Supported by Lee and Khang (2012), CNT is one of the most promising and practical applications of CNTs is their use as reinforcing filler in polymer matrices, with the outstanding improvement in mechanical properties due to their excellent chemical and physical properties such as strength and modulus.

Numerous experiments were conducted to study the properties of the interaction between NR and PLA incorporate with compatibilizers and also its nanocomposites. Corresponding with this, limited research has been carried out to understanding the rheology behaviour of polymers and their nanocomposites which highly useful for predicting the processing behaviour of PLA and its nanocomposites. Studies related to rheological behaviour of pure polymeric melts are well documented, while such studies on molten polymer blends and its nanocomposite are relatively limited, but are indispensable (Djellali *et al.*, 2015). Therefore, study related to understanding rheology behaviour of polymer melt and its nanocomposite was conducted. Accordingly, constitutive equations found in the literature that adequately describe polymer melt will be explored for their application in polymer blends and nanocomposites processing. Particular focus will be given in this project to nonlinear rheological characteristics of viscoelastic materials. For this reason, rheological mathematical models presented by power law model and Carreau – Yasuda model were applied in this particular study to describe the rheological characteristic of the polymer melt.

1.3 Research Objectives

The main objective of this research is to study fundamental science and interaction mechanism of biopolymeric nanocomposite system.

- i. To investigate the effects of toughening agent (natural rubber) with different loading on mechanical, thermal, rheological and morphological properties in PLA/NR/CNT blend.
- ii. To investigate the effect of compatibilizers (NR-g-MA and PLA-g-MA) on mechanical, thermal, rheological and morphological properties in the PLA/NR blend.
- iii. To analyse the effects of different pristine CNT amount on mechanical, thermal, morphological and rheological properties of PLA/NR/Compatibilizers/CNT nanocomposite blend.
- iv. To analyse the rheological characteristic of the PLA/NR/CNT with respect to contributions of the materials composition towards the rheological properties by using rheological mathematical models.

1.4 Scopes of Research

In order to achieve the objectives of the research the following scopes of work have been performed:

- i. Sample preparations

Sample preparations in this study were involved preparing various samples of polymer blends using different ratio of NR ranging from 5% - 20% and CNT loading (1 - 8 phr). These involved compounding process from raw material feeding, extrusion, pelletizing and compression moulding according to the following sections:

- i. PLA/NR blend
 - ii. Synthesis of compatibilizers (PLA-g-MA and NR-g-MA)
 - iii. PLA/NR/Compatibilizer blend
 - iv. PLA/NR/Compatibilizer/CNT nanocomposite

- ii. Perform analysis and characterizations:
 - i. Mechanical Test

Evaluation of toughening effect by conducted Izod Impact test to study the effect of NR and compatibilizer ratio. Tensile test and flexural test also were conducted to study the effect in additional of NR and CNT loading on strength and stiffness of materials.

 - ii. Thermal properties analysis

Determination of thermal behaviour differential scanning calorimetry (DSC) and thermalgravimetric analysis (TGA) were conducted to analyse glass transition temperature, melting temperatute, percentage of crystallinity, degradation temperature and thermal stability of materials.

 - iii. Characterizations and morphological study

Scanning electron microscopy (SEM), NanoScanning electron microscopy (NanoSEM) and X-ray diffraction (XRD) analysis were carried out to characterize the morphology of the blends and to investigate the interfacial bonding and distribution between PLA/NR/Compatibilizer/CNT.

 - iv. Rheological properties analysis

Melt Flow Index (MFI) analysis was run to measure the ability of the materials's melt to flow under pressure and to determine the processing condition for material blends. Rotational rheometer was conducted to discover the rheological properties of PLA/NR/compatibilizer blends. Some important data was collected such as G' , G'' and complex viscosity as these data were used in modelling approaches.

v. Rheological Mathematical Models

Based on experimental data obtained from rheological analysis, Power Law models and Carreau – Yasuda model were used to obtain mathematical data to describe the rheological characteristic of the polymer melt. Both experimental and mathematical data were compared and analysed the suitability between both data. In this study, rheological theoretical models were approached to predicting the shear-thinning nonlinear rheological behaviour of materials on the effect of additional natural rubber and CNT as nanofiller.

REFERENCES

- Abbasi, S., Carreau, P. J. and Derdouri, A. (2010). Flow Induced Orientation of Multiwalled Carbon Nanotubes In Polycarbonate Nanocomposites: Rheology, Conductivity and Mechanical Properties. *Polymer*. 51 (4), 922-935.
- Abdel-Goad, M. and Pötschke, P. (2005). Rheological characterization of melt processed polycarbonate-multiwalled carbon nanotube composites. *Journal of Non-Newtonian Fluid Mechanics*. 128 (1), 2-6.
- Abdel-Khalik, S. I., Hassager, O., and Bird, R. B. (1974). Prediction of melt elasticity from viscosity data. *Polymer Eng. and Sci.* 14, 859–867.
- Abdullah Sani, N. S. (2015). *Effects of compatibilizer on morphology, mechanical and thermal properties of Polylactic Acid/ Natural rubber blend*. Master Thesis, Universiti Teknologi Malaysia, Skudai.
- Abdullah, N.A.S., Mohamad, Z. (2018). The effect of dynamic vulcanization on the morphological and mechanical properties of the toughened poly (lactic acid)/epoxidized natural rubber. *Malaysian Journal of Fundamental and Applied Sciences*. 14 (3).
- Abraham, J., Sharika, T., George, S. C. and Thomas, S. (2017) Rheological Percolation in Thermoplastic Polymer Nanocomposites, *Rheology*. 1 (1), 3-15.
- Alig, I., Pötschke, P., Lellinger, D., Skipa, T., Pegel, S., Kasaliwal, G. R., Villmowb, T. (2012). Establishment, Morphology and Properties of Carbon Nanotube Networks In Polymer Melts. *Polymer*. 53 4-28.
- Arsad, A., (2010). Compatibiliser effects on properties of polyamide-6/acrylonitrile-butadiene-styrene and polyamide-6/acrylonitrile-butadiene-styrene/short glass fibre thermoplastic composites. PhD Thesis. Universiti Teknologi Malaysia, Skudai.
- Auras, R., Harte, B. and Selke, S. (2004). An Overview of Polylactides as Packaging Materials. *Macromolecular Bioscience*. (4) 835–864.
- Averous, L. (2004). Biodegradable Multiphase Systems Based on Plasticized Starch: A Review. *Journal of Macromolecular Science: Part C*. 44 (3), 231–274.

- Aziz, A. A., Abang Ismawi Hassim D. H., Suriani, A. B. and Mahmood, M. R. (2014). Effect of Multi- Wall Carbon Nanotubes on the Properties of Natural Rubber Nanocomposites *Advanced Materials Research*. 832, 338-343.
- Baouz, T., Rezgui, F. and Yilmazer, U. (2012). Ethylene-Methyl Acrylate-Glycidyl Methacrylate Toughened Poly(lactic acid) Nanocomposites. *Journal of Applied Polymer Science*.
- Barnes, H.A., Hutton, J. F., and Walters, K. (1989). *An Introduction to Rheology*, Elsevier Science Publishers B.V., Amsterdam, The Netherlands.
- Basuli, U., Chaki, T. K. and Chattopadhyay, S. (2012). Mechanical, Thermal, And Rheological Behavior of Ethylene Methyl Acrylate-MWNT Nanocomposites. *Polymer Engineering and Science*. 52 (2), 277-288.
- Bijarimi, M., Ahmad, S., Rasid, R., (2012) Mechanical, thermal and morphological properties of poly(lactic acid)/epoxidized natural rubber blends. *Journal of Elastomers & Plastics*, 1–17.
- Bitinis, N., Verdejo, R., Cassagnau, P., Lopez-Manchado, M.A. (2011), Structure and Properties of Polylactide/Natural Rubber Blends. *Materials Chemistry and Physics*. 129, 823– 831.
- Björn, A., de La Monja, P. S., Karlsson, A., Ejlertsson, J. and Svensson, B. H. (2012), Rheological Characterization, INTECH, 63-76.
- Bokobza, L. and M. Kolodziej, (2006) On The Use Of Carbon Nanotubes As Reinforcing Filler For Elastomeric Materials. *Polymer International*. 55 (9), 1090-1098.
- Bokobza, L. (2012). Enhanced electrical and mechanical properties of multiwall carbon nanotube rubber composites. *Polymers for Advanced Technologies*. 23 (12), 1543-1549.
- Bordes, P., Pollet, E. and Avérous, L. (2009). Nano-biocomposites: Biodegradable polyester/nanoclay Systems. *Progress in Polymer Science*. 34 (2), 125-155.
- Bourbigot, S., Fontaine, G. I., Gallosa, A. and Bellayer, S. v. (2011). Reactive extrusion of PLA and of PLA/carbon nanotubes nanocomposite: processing, characterization and flame retardancy. *Polymer Advanced Technologies*. 22 30-37.
- Buys, Y.F., Aznan, A.N.A., Anuar, H. (2018) Mechanical properties, morphology, and hydrolytic degradation behavior of polylactic acid / natural rubber blends, IOP Conf. Series: Materials Science and Engineering 290.

- Byrne, M.T. and Gun'ko, Y.K. (2010) Recent Advances in Research on Carbon Nanotube-Polymer Composites. *Advanced Materials*. 22, 1672-1688
- Carlson, D., Nie, L., Narayan, R., Dubois, P. (1999) Maleation of polylactide (PLA) by reactive extrusion. *Journal of Applied Polymer Science*. 72 (4), 477-485.
- Carone Jr, E., Kopcak, U., Goncalves, M.C., Nunesb, S.P. (2000). In Situ Compatibilization of Polyamide 6/Natural Rubber Blends With Maleic Anhydride. *Polymer*. 41 5929–5935.
- Cao, X. V., Ismail, H., Rashid, A. A., Takeichi, T., and Vo-Huu, T. (2012) Maleated Natural Rubber as a Coupling Agent for Recycled High Density Polyethylene/Natural Rubber/Kenaf Powder Biocomposites. *Polymer-Plastics Technology and Engineering*. 51 (9), 904-910.
- Chen, J., Shi, Y.Y., Yang, J.H., Zhang, N., Huang, T., Wang, Y. (2013) Improving Interfacial Adhesion Between Immiscible Polymers by Carbon Nanotube. *Polymer*. 54 (1), 464-471.
- Cherizol, R., Sain, M., Tjong, J. (2015). Review of Non-Newtonian Mathematical Models for Rheological Characteristics of Viscoelastic Composites, *Green and Sustainable Chemistry*, 5, 6-14.
- Chiu, W.-M., Chang, Y.-A., Kuo, H.-Y., Lin, M.-H. and Wen, H.-C. (2008). A study of carbon nanotubes/biodegradable plastic polylactic acid composites. *Journal of Applied Polymer Science*. 108 (5), 3024-3030.
- Choi, C. S., Park, B. J. and Choi, H. J. (2007). Electrical and rheological characteristics of poly(vinyl acetate)/multi-walled carbon nanotube nanocomposites. *Diamond and Related Materials*. 16 (4–7), 1170-1173.
- Chow, W.S., Abu Bakar, A., Mohd Ishak, Z.A., Karger-Kocsis, J., Ishiaku, U.S. (2005) Effect of Maleic Anhydride Grafted Ethylene—Propylene Rubber on the Mechanical, Rheological and Morphological Properties of Organoclay Reinforced Polyamide 6/Polypropylene. *European Polymer Journal*. 41 (4), 687-696.
- Cipriano, T.F., Nazreth da Silva, A.L., Fonseca Thome da Silva, A.H.M., Furtado de Sousa, A.M., Monteiro da Silva, G., Rocha, M.G. (2014) Thermal, rheological and morphological properties of poly(lactic Acid) (PLA) and talc composites. *Polimeros*. 24 (3), 276-282.

- Coleman, J. N., Khan, U., Blau, W. J. and Gun'ko, Y. K. (2006). Small But Strong: A Review of The Mechanical Properties of Carbon Nanotube–Polymer Composites. *Carbon*. 44 (9), 1624-1652.
- Datta, R. and Henry, M. (2006). Lactic Acid: Recent Advances In Products, Processes and Technologies – A Review. *Journal of Chemical Technology and Biotechnology*. 81 1119–1129.
- Datta, P., Guha, C. and Sarkhel, G. (2015). Mechanical, rheological, and electrical properties of multiwalled carbon nanotube reinforced ASA/Na-ionomer blend. *Journal of Applied Polymer Science*. 132 (36).
- Djellali, S., Sadoun, T., Haddaoui, N., Bergeret, A., (2015), Viscosity and viscoelasticity measurements of low density polyethylene/poly(lactic acid) blends, *Polymer Bulletin* 72(5).
- Drumright, R. E., Gruber, P. R. and Henton, D. E. (2000). Polylactic Acid Technology. *Advanced Materials*. 12 (23), 1841-1846.
- Elias, L., Fenouillot, F., Majeste, J. C. and Cassagnau, P. (2007). Morphology and Rheology of Immiscible Polymer Blends Filled With Silica Nanoparticles. *Polymer*. 48 (20), 6029-6040.
- Eken, A. E., Tozzi, E. J., Klingenberg, D. J. and Bauhofer, W. (2012). Combined Effects of Nanotube Aspect Ratio and Shear Rate On The Carbon Nanotube/Polymer Composites. *Polymer*. 53 4493-4500.
- Fan, Z. and Advani, S.G. (2007) Rheology of multiwall carbon nanotube suspensions. *Journal of Rheology*. 51 (4), 585-604.
- Faruk, O., Bledzki, A.K., Fink, H. P., Sain, M. (2012). Biocomposites Reinforced With Natural Fibers: 2000–2010. *Progress in Polymer Science*. 37 1552–1596.
- Fukushima, K., Abbate, C., Tabuani, D., Gennari, M. and Camino, G. (2009). Biodegradation of Poly(Lactic Acid) and Its Nanocomposites. *Polymer Degradation and Stability*. 94 (10), 1646-1655.
- Garlotta, D. (2001). A Literature Review of Poly(Lactic Acid). *Journal of Polymers and the Environment*. 9 (2), 63-84.
- Gleinser, W., Braun, H., Friedrich, C. and Cantow, H. J. (1994). Correlation Between Rheology and Morphology of Compatibilized Immiscible Blends. *Polymer*. 35 (1), 128-135.

- Hajba, S., and Tabi, T., (2017). Polylactic acid / Natural Rubber Blends, *Material Science Forum*, 885, 298-302.
- Hamad, K., Kaseem, M., Deri, F., (2011), Melt Rheology of Poly(Lactic Acid)/Low Density Polyethylene Polymer Blends, *Advances in Chemical Engineering and Science*, 1, 208-214.
- Han, Z., and Fina, a. (2011) Thermal Conductivity of Carbon Nanotubes and Their Polymer Nanocomposites : A Review. *Progress in Polymer Science*. 36, 914-944.
- Hartmann, M. H., (1998) ‘‘High MolecularWeight Polylactic Acid Polymers’’, in: Biopolymers from Renewable Resources, 1st edition, D. L. Kaplan, Ed., Springer-Verlag Berlin Heidelberg, Berlin, 367–411.
- Hapuarachchi, T. D., Bilotti, E., Reynolds, C. T. and Peijs, T. (2011). The Synergistic Performance of Multiwalled Carbon Nanotubes and Sepiolite Nanoclays as Flame Retardants for Unsaturated Polyester. *Fire and Materials*. 35 (3), 157-169.
- Hapuarachchi, T. D. and Peijs, T. (2010). Multiwalled carbon nanotubes and sepiolite nanoclays as flame retardants for polylactide and its natural fibre reinforced composites. *Composites Part A: Applied Science and Manufacturing*. 41 (8), 954-963.
- Huneault, M.A. and Li, H., (2007) Morphological and properties of compatibilized polylactide/thermoplastic starch blends. *Polymer* 48 (1), 270-280.
- Hwang, S. W., Lee, S. B., Lee, C. K., Lee, J. Y., Shim, J. K., Selke, S. E. M., Soto-Valdez, H., Matuana, L., Rubino, M. and Auras, R. (2012). Grafting Of Maleic Anhydride On Poly(L-Lactic Acid). Effects On Physical and Mechanical Properties. *Polymer Testing*. 31 (2), 333-344.
- Ishida, S., Nagasaki, R., Chino, K., Dong, T. and Inoue, Y. (2009). Toughening of Poly(L-Lactide) By Melt Blending With Rubbers. *Journal of Applied Polymer Science*. 113 (1), 558-566.
- Ismail, H., Rusli, A. and Rashid, A. A. (2005). Maleated Natural Rubber as A Coupling Agent for Paper Sludge Filled Natural Rubber Composites. *Polymer Testing*. 24 (7), 856-862.
- Iwatake, A., Nogi, M. and Yano, H. (2008). Cellulose Nanofiber-Reinforced Polylactic Acid. *Composites Science and Technology*. 68 (9), 2103-2106..

- Jaratrotkamjorn, R., Khaokong, C. and Tanrattanakul, V. (2012). Toughness Enhancement of Poly(Lactic Acid) by Melt Blending With Natural Rubber. *Journal of Applied Polymer Science*. 124 (6), 5027 - 5036.
- Jia, Y., Peng, K., Gong, X.-l. and Zhang, Z. (2011). Creep and Recovery of Polypropylene/Carbon Nanotube Composites. *International Journal of Plasticity*. 27 (8), 1239-1251.
- Jiang, L., Zhang, J. and Wolcott, M. P. (2007). Comparison of Polylactide/Nano-Sized Calcium Carbonate and Polylactide/Montmorillonite Composites: Reinforcing Effects and Toughening Mechanisms. *Polymer*. 48 (26), 7632-7644.
- Juntuek, P., Ruksakulpiwat, C., Chumsamrong, P. and Ruksakulpiwat, Y. (2012). Effect of Glycidyl Methacrylate-Grafted Natural Rubber On Physical Properties of Polylactic Acid and Natural Rubber Blends. *Journal of Applied Polymer Science*. 125 (1), 745-754.
- Kaci, M., Zaidi, L., Bruzaud, S. Bourmaud, A., Mederic, P. and Grohens, Y. (2012). Influence of loading rates on morphological and mechanical properties of PLA/clay nanocomposites. *Int. J. Microstructure and Materials Properties*, 7, (5), 390–399.
- Kashiwagi, T., Grulke, E., Hilding, J., Groth, K., Harris, R., Butler, K., Shields, J., Kharchenko, S. and Douglas, J. (2004). Thermal and flammability properties of polypropylene/carbon nanotube nanocomposites. *Polymer*. 45 (12), 4227-4239.
- Kaseem, M., Ko, Y.G., (2017), Melt Flow Behavior and Processability of Polylactic Acid/ Polystyrene (PLA/PS) Polymer Blends, *Journal Polymer Environment* 25: 994.
- Kim, J.Y. and Kim, S.H. (2012) High Performance PET/Carbon Nanotube Nanocomposites: Preparation, Characterization, Properties and Applications. *Nanocomposites New Trends Dev* 51.
- Krägel, J. and Derkatch, S. R. (2010). Interfacial Shear Rheology. *Current Opinion in Colloid & Interface Science*. 15 (4), 246-255.
- Kricheldorf, H. R., Berl, M. and Scharnagl, N. (1988). Poly(Lactones). 9. Polymerization Mechanism of Metal Alkoxide Initiated Polymerizations of Lactide And Various Lactones. *Macromolecules*. 21 (2), 286-293.

- Kuan, C.-F., Kuan, H.-C., Ma, C.-C. M. and Chen, C.-H. (2008). Mechanical and Electrical Properties of Multi-Wall Carbon Nanotube/Poly(Lactic Acid) Composites. *Journal of Physics and Chemistry of Solids*. 69 (5–6), 1395-1398.
- Kumar, P., Sandeep, K. P., Alavi, S., Truong, V. D. and Gorga, R. E. (2010). Preparation and Characterization of Bio-Nanocomposite Films Based On Soy Protein Isolate And Montmorillonite Using Melt Extrusion. *Journal of Food Engineering*. 100 (3), 480-489.
- Kuila, T., Bose, S., Khanra, P., Kim, N.H., Rhee, K.Y., Lee, J.H. (2011) Characterization and properties of in situ emulsion polymerized poly(methyl methacrylate)/ graphene nanocomposites. *Composites Part A: Applied Science and Manufacturing*. 42 (11), 1856-1861.
- Le Marec, P. E., Quantin, J.-C., Ferry, L., Bénézet, J.-C., Guilbert, S. and Bergeret, A. (2014). Modelling of PLA melt rheology and batch mixing energy balance. *European Polymer Journal*. 60 273-285.
- Lee, Jung-Bea and Khang, Dahl-Young, (2012). Electrical and mechanical characterization of stretchable multi-walled carbon nanotubes/polydimethylsiloxane elastomeric composite conductors. *Composites Science and Technology* 72, 1257–1263
- Launay, B., Doublier, J. L., and Cuvelier, G. 1986. Flow properties of aqueous solutions and dispersions of polysaccharides, *Functional Properties of Food Macromolecules*, Elsevier Applied Science Publishers, London, 1–78.
- Li, J., (2017). Multiwalled Carbon Nanotubes Reinforced Polypropylene Composite Material, *Journal of Nanomaterials* Volume 2017, 5 .
- Li, W.-H., Chen, X.-H., Chen, C.-S., Xu, L.-S., Yang, Z. and Wang, Y.-G. (2008). Preparation and Shear Properties of Carbon Nanotubes/Poly(Butyl Methacrylate) Hybrid Material. *Polymer Composites*. 29 (9), 972-977.
- Lim, L. T., Auras, R. and Rubino, M. (2008). Processing Technologies for Poly(Lactic Acid). *Progress in Polymer Science*. 33 (8), 820-852.
- Liu, J., Zhang, L., Cao, D. and Wang, W. (2009). Static, rheological and mechanical properties of polymer nanocomposites studied by computer modeling and simulation. *Physical Chemistry Chemical Physics*. 11 (48), 11365-11384.

- Liu, Y. and Gao, L. (2005). A Study of The Electrical Properties of Carbon Nanotube-NiFe₂O₄ Composites: Effect Of The Surface Treatment of The Carbon Nanotubes. *Carbon*. 43 (1), 47-52.
- Liu, H. and Zhang, J. (2011). Research Progress In Toughening Modification of Poly(Lactic Acid). *Journal of Polymer Science Part B: Polymer Physics*. 49 (15), 1051-1083.
- Liu, M.-J., Chen, S.-C., Yang, K.-K. and Wang, Y.-Z. (2015). Biodegradable polylactide based materials with improved crystallinity, mechanical properties and rheological behaviour by introducing a long-chain branched copolymer. *RSC Advances*. 5 (52), 42162-42173.
- Liu, X.-Q., Li, R.-H., Bao, R.-Y., Jiang, W.-R., Yang, W., Xie, B.-H. and Yang, M.-B. (2014). Suppression of phase coarsening in immiscible, co-continuous polymer blends under high temperature quiescent annealing. *Soft Matter*. 10 (20), 3587-3596.
- Lopes da Silva, J. A. L., Gonçalves, M. P., and Rao, M. A. (1992). Rheological properties of high-methoxyl pectin and locust bean gum solutions in steady shear. *J. Food Sci.* 57, 443–448.
- Lu, M., Keskkula, H. and Paul, D. R. (1995). Toughening of Nylon 6 With Grafted Rubber Impact Modifiers. *Journal of Applied Polymer Science*. 58 (7), 1175-118.
- Ma, P., Hristova-Bogaerds, D.G., Goossens, J.G.P., Spoelstra, A.B., Zhang, Y., Lemstra, P.J.(2012) Toughening of poly(lactic acid) by ethylene co-vinyl acetate copolymer with different vinyl acetate contents. *European Polymer Journal*. 48 (1), 146-154 .
- Mark, H.F., (1970) *Encyclopedia of Polymer Science and Engineering*, Wiley: New York, 492 .
- Martin, O. and Averous, L. (2001). Poly(Lactic Acid): Plasticization And Properties and Properties of Biodegradable Multiphase System. *Polymer*. 42 6209-6219.
- Mat Desa, M. S. Z., Hassan, A. and Arsad, A. (2013). The Effect of Natural Rubber Toughening on Mechanical Properties of Poly(lactic Acid)/ Multiwalled Carbon Nanotube Nanocomposite. *Advanced Materials Research*. 747, 639-642.

- Meinander, K., Niemi, M., Hakola, J. S. and Selin, J.-F. (1997). Polylactides - Degradable Polymers for Fibres and Films. *Macromolecular Symposia*. 123 (1), 147-153.
- Mortazavi, S., Ghasemi, I. and Oromiehie, A. (2014). Morphological and rheological properties of (low-density polyethylene)/thermoplastic starch blend: investigation of the role of high elastic network. *Journal of Vinyl and Additive Technology*. 20 (4), 250-259.
- Mohamad, N., Muchtar, A., Ghazali, M.J. Hj Mohd, D., Azhari, C.H. (2008) The effect of filler on epoxidised natural rubber-alumina nanoparticles composites. *European Journal of Scientific Research*. 24 (4), 538-547.
- Murariu, M., Da Silva Ferreira, A., Degée, P., Alexandre, M. and Dubois, P. (2007). Polylactide Compositions. Part 1: Effect of Filler Content and Size On Mechanical Properties of PLA/Calcium Sulfate Composites. *Polymer*. 48 (9), 2613-2618.
- Nabil, H, Ismail, H , Azura, A.R., (2014). Thermal Stability and Aging Characteristics of (Natural/Rubber)/(Waste Ethylene-Propylene-Diene Monomer Terpolymer) Blend, volume 20, (2), 99-107.
- Nakason, C., Kaesaman, A. and Supasanthitikul, P. (2004). The Grafting of Maleic Anhydride Onto Natural Rubber. *Polymer Testing*. 23 35-41.
- Nakason, C., Saiwaree, S., Tatun, S. and Kaesaman, A. (2006). Rheological, Thermal and Morphological Properties of Maleated Natural Rubber and Its Reactive Blending With Poly(Methyl Methacrylate). *Polymer Testing*. 25 (5), 656-667.
- Nield, S.A., Budman, H.M., Tzoganakis, C. (2000). Control of a LPDE reactive extrusion process. *Control Engineering Practice*, 8, 911
- Njuguna, J., Pielichowski, K. and Desai, S. (2008). Nanofiller-Reinforced Polymer Nanocomposites. *Polymers for Advanced Technologies*. 19 (8), 947-959.
- Oksman, K., Skrifvars, M., Selin, J. -F. (2003). Natural fibres as reinformant in polylactic acid (PLA) composites. *Composites Science and Technology*. 63 (9), 1317-1324.
- Othman, M. Tan, K. H., Mohd Yusof, H., Halisanni, K., Ruzaidi, G., Nazarudin, Z., Paridah, T., Noor Azlina, H. (2013) Effects of Multi-Walled Carbon Nanotubes (MWCNTS) On the Mechanical and Thermal Properties of Plasticized Polylactic Acid Nanocomposites). *Advanced Materials Research*. 812, 181-186

- Pack, S., Kashiwagi, T., Stemp, D., Koo, J., Si, M., Sokolov, J. C. and Rafailovich, M. H. (2009). Segregation of Carbon Nanotubes/Organoclays Rendering Polymer Blends Self-Extinguishing. *Macromolecules*. 42 (17), 6698-6709.
- Papageorgiou, G.Z., Achilias, D.S., Bikiaris, D.N., Nanaki, S. (2010) PLA nanocomposites: Effect of filler type on non-isothermal crystallization. *Thermochimica Acta*. 511 (1), 129-139.
- Paradise, M., Goswami, T. (2007). Carbon Nanotubes – Production And Industrial Applications. *Materials and Design*. 28 1477–1489.
- Paul, D. R. and Robeson, L. M. (2008). Polymer nanotechnology: Nanocomposites. *Polymer*. 49 (15), 3187-3204.
- Paul, D., Newman, S., (1978) Polymer Blends, Academic Press, USA
- Park, S. G., Abdal-hay, A., Abdel-Jaber, G. T., Lim, J. K. (2013) Biodegradable Poly(Lactic Acid)/Multiwalled Carbon Nanotube Nanocomposites Fabrication Using Casting And Hot Press Technique, *International Journal of Innovative Research in Science, Engineering and Technology*. 2 (12), 7976-7981.
- Picchi, D., Barmak, I., Ullmann, A. and Brauner, N. (2018). Stability of stratified two-phase channel flows of Newtonian/non-Newtonian shear-thinning fluids. *International Journal of Multiphase Flow*. 99, 111-131
- Pinarbasi, A. and Liakopoulus, A. (1995). Stability of two layer Poissullei flow of Carreau yasuda and Bingham-like fluids. *Journal of Non-Newtonian Fluid Mechanics*. 57, (2–3). 227-241
- Pinto, V. C., Tiago Ramos, Sofia Alves, J. Xavier, Paulo Tavares, P. M. G. P. Moreira, Rui Miranda Guedes. (2015) Comparative failure analysis of PLA, PLA/GNP and PLA/CNTCOOH biodegradable nanocomposites thin films, *Procedia Engineering* 114, 635 – 642
- Petersson, L., Oksman, K. and Mathew, A. P. (2006). Using Maleic Anhydride Grafted Poly(Lactic Acid) as A Compatibilizer In Poly(Lactic Acid)/Layered-Silicate Nanocomposites. *Journal of Applied Polymer Science*. 102 (2), 1852-1862.
- Pevere, Å.; Guibad, G; van Hullenbusch, E.; Lens, P. & Baudu, M. (2006). Viscosity evolution of anaerobic granular sludge. *Biochem Engineering Journal*, 27, 315-322.

- Pluta, M., Galeski, A., Alexandre, M., Paul, M. A. and Dubois, P. (2002). Polylactide/Montmorillonite Nanocomposites and Microcomposites Prepared by Melt Blending: Structure and Some Physical Properties. *Journal of Applied Polymer Science*. 86 (6), 1497-1506.
- Pongtanayut, K., Thongpin, C. and Santawitee, O. Effect of Rubber on Morphology, Thermal Properties and mechanical Properties of PLA/NR and PLA/ENR blends. (2013) *Energy Procedia*. 34 , 888-897.
- Porter, K., (2006). Ring Opening Polymerization of Lactide for the Synthesis of *Polylactic Acid A., comp.*
- Poslinski, A. J., Ryan, M. E., Gupta, R. K., Seshadri, S. G., and Frechette, F. J. (1988). Rheological behavior of filled polymeric systems I. Yield stress and shear-thinning effects. *J. Rheol.* 32: 703–735
- Prasantha, K., Krawczak, P., Lecouvet, B., Sclavons, M. (2012) Poly(lactic acid)/halloysite nanotubes nanocomposites: Structure, thermal and mechanical properties as a function of halloysite treatment. *Journal of Applied Polymer Science*. 128 (3)
- Putz, K. W., Palmeri, M. J., Cohn, R. B., Andrews, R. and Brinson, L. C. (2008). Effect of Cross-Link Density On Interphase Creation In Polymer Nanocomposites. *Macromolecules*. 41 (18), 6752-6756.
- Qiu, W., Endo, T. and Hirotsu, T. (2005). A Novel Technique for Preparing of Maleic Anhydride Grafted Polyolefins. *European Polymer Journal*. 41 (9), 1979-1984.
- Rathi, S., Chen, X., Coughlin, E. B., Hsu, S. L., Golub, C. S. and Tzivanis, M. J. (2011). Toughening Semicrystalline Poly(Lactic Acid) By Morphology Alteration. *Polymer*. 52 (19), 4184-4188.
- Rao, M. A. (2007). Flow and Functional Models for Rheological Properties of Fluid. *Foods, Rheology of Fluid and Semisolid Foods*. 27-58.
- Rao, M. A. (2014). Rheology of Fluid, Semisolid, and Solid Foods, *Food Engineering Series*, 1571-0297.
- Raquez, J.-M., Narayan, R. and Dubois, P. (2008). Recent Advances In Reactive Extrusion Processing of Biodegradable Polymer-Based Compositions. *Macromolecular Materials and Engineering*. 293 (6), 447-470.

- Ray, S.S. and Okamoto, M. (2003) Polymer/Layered silicate Nanocomposites: A review from preparation to processing. *Progress in Polymer Science*. 28, 1539--1641.
- Sadiku-Agboola, O., Sadiku, E. R., Adegbola, A. T. and Biotidara, O. F. (2011). Rheological Properties of Polymers: Structure and Morphology of Molten Polymer Blends. *Materials Sciences and Applications*. 02 (01), 30-41.
- Saelao, J. and Phinyocheep, P. (2005). Influence of Styrene On Grafting Efficiency of Maleic Anhydride onto Natural Rubber. *Journal of Applied Polymer Science*. 95 (1), 28-38.
- Saki, T.A. (2015) Reactive melt blending of low-density polyethylene with poly (acrylic acid), *Arabian Journal of Chemistry*. 8 (2), 191-199.
- Schramm, G. (2000). A practical approach to rheology and rheometry. *Thermo HAAKE Rheology, Germany*.
- Shaffer, M. S. P., & Windle, A. H. (1999). Fabrication and Characterization of Carbon Nanotube/Poly(vinyl alcohol) *Composites Advance Materials*, 11, 937-941.
- Seligra, P. G., Lamanna, M. and Famá, L. (2015). Promising PLA-functionalized MWCNT composites to use in nanotechnology. *Polymer Composites*. 37 (10), 3066 - 3072.
- Seyssiecq, I.; Ferasse, J.H. & Roche, N. (2003). State-of-the-art: rheological characterization of waste water treatment sludge. *Biochem Engineering Journal*. 16, 41-56.
- Södergård, A. and Stolt, M. (2002). Properties of Lactic Acid Based Polymers and Their Correlation With Composition. *Progress in Polymer Science*. 27 (6), 1123-1163.
- Sombatsompop, N., Rungrattawachai, P., Bouvaree, N. and Eaksrisakul, K. (2001). Material Behaviour: Effect Of Mastication Time On Flow Patterns Of Natural Rubber In The Barrel Of A Capillary Rheometer. *Polymer Testing*. 20 (3), 317-320.
- Sookprasert, P., (2017). Morphology, mechanical and thermal properties of poly(lactic acid) (PLA)/natural rubber (NR) blends compatibilized by NR-graft-PLA, *J. Mater. Res.*, Vol. 32, No. 4.

- Spitalsky, Z., Tasis, D., Papagelis, K., Galiotis, C. (2010) Carbon nanotube-polymer composites: Chemistry, processing, mechanical and electrical properties. *Progress in Polymer Science*. 35 (3), 357--401.
- Sundararaj. U. and Macosko. C.W. (1995) Drop Breakup and Coalescence in Polymer Blends: The Effects of Concentration and Compatibilization. *Macromolecules* 28 (8), 2647- 2657.
- Sunthar, P., (2009). Polymer Simulations Companion: An Introduction to Brownian Dynamics.
- Tanrattanakul, V., Sungthong, N., and Raksa, P. (2008) Rubber toughening of nylon 6 with epoxidized natural rubber. *Polymer Testing* 27 (7): 794-800.
- Teng, C.-C., Ma, C.-C. M., Huang, Y.-W., Yuen, S.-M., Weng, C.-C., Chen, C.-H. and Su, S.-F. (2008). Effect Of MWCNT Content On Rheological and Dynamic Mechanical Properties of Multiwalled Carbon Nanotube/Polypropylene Composites. *Composites: Part A*. 39 1869–1875.
- Thostenson, E. T., Ren, Z. and Chou, T.-W. (2001). Advances In The Science and Technology of Carbon Nanotubes and Their Composites: A Review. *Composites Science and Technology*. 61 (13), 1899-1912.
- Thostenson, E. T., Li, C. and Chou, T.-W. (2005). Nanocomposites In Context. *Composites Science and Technology*. 65 (3–4), 491-516.
- Unnikrishnan, V. and Reddy, J. N. (2012). Multiscale Analysis of the Core Nanotube In A Nanocomposite System. *Finite Elements in Analysis and Design*. 49 (1), 13-18.
- Wang, Z.F., Peng, Z., Li, S.D., Lin, H., Zhang, K.X., She, X.D., Fu, X., (2009) The Impact of Esterification on the Properties of Starch/Natural Rubber Composite. *Composite Science and Technology*. 69 (11-12), 1797-1803.
- Wu, C.-S. and Liao, H.-T. (2007). Study on the preparation and characterization of biodegradable polylactide/multi-walled carbon nanotubes nanocomposites. *Polymer*. 48 (15), 4449-4458
- Xie, D., Zhao, Y., Li, Y., LaChance, A.M., Lai, J., Sun L. and Chen, J., (2019) Rheological, Thermal, and Degradation Properties of PLA/PPG Blends. *Materials*, 12, 3519
- Xu, C., Yuan, D., Fu, L., Y. Chen, Y. (2014) Physical blend of PLA/NR with co-continuous phase structure: Preparation, rheology property, mechanical properties and morphology. *Polymer Testing* 37, 94-101.

- Xu, D. and Wang, Z. (2008). Role of multi-wall carbon nanotube network in composites to crystallization of isotactic polypropylene matrix. *Polymer*. 49 (1), 330-338.
- Xu, Z., Niu, Y., Yang, L., Xie, W., Li, H., Gan, Z. and Wang, Z. (2010). Morphology, rheology and crystallization behavior of polylactide composites prepared through addition of five-armed star polylactide grafted multiwalled carbon nanotubes. *Polymer*. 51 (3), 730-737.
- Yang, D. J. and Lin, Y. H. (2003). Brownian dynamics simulations of the effects of hydrodynamic interactions on the polymer viscoelastic behavior. *Polymer*. 44 (9), 2807-2815.
- Yang, K.-K., Wang, X.-L. and Wang, Y.-Z. (2007). Progress in Nanocomposite of Biodegradable Polymer. *Journal of Industrial and Engineering Chemistry*. 13 485-500.
- Yeh, M.-K., Tai, N.-H. and Liu, J.-H. (2006). Mechanical Behavior of Phenolicbased Composites Reinforced With Multi-Walled Carbon Nanotubes. *Carbon*. 44 (1), 1-9.
- Ying-Chen, Z., Hong-Yan, W. and Yi-Ping, Q. (2010). Morphology and Properties of Hybrid Composites Based On Polypropylene/Polylactic Acid Blend and Bamboo Fiber. *Bioresource Technology*. 101 (20), 7944-7950.
- Yokohara, T. and Yamaguchi, M. (2008). Structure And Properties For Biomass-Based Polyester Blends of PLA And PBS. *European Polymer Journal*. 44 (3), 677-685
- Yoon, J. T., Jeong, Y. G., Lee, S. C. and Min, B. G. (2009). Influences of Poly(Lactic Acid)-Grafted Carbon Nanotube On Thermal, Mechanical, and Electrical Properties of Poly(Lactic Acid). *Polymers for Advanced Technologies*. 20 (7), 631-638.
- Yu, L., Dean, K.M., Li, L., (2006) Polymer Blends And Composites From Renewable Resources. *Progress in Polymer Science*. 31 (6): 576-602.
- Zachariah, A. K., Geethamma, V. G., Chandra, A. K., Mohammed, P. K. and Thomas, S. (2014). Rheological behaviour of clay incorporated natural rubber and chlorobutyl rubber nanocomposites. *RSC Advances*. 4 (101), 58047-58058.

- Zare, Y., Park, S.P., Rhee, K.Y. (2019), Analysis of complex viscosity and shear thinning behaviour in poly (lactic acid)/poly (ethylene oxide)/carbon nanotubes biosensor based on Carreau–Yasuda model, *Physics* 13.
- Zhang, C., Man, C., Pan, Y., Wang, W., Jiang, L. and Dan, Y. (2011). Toughening of polylactide with natural rubber grafted with poly(butyl acrylate). *Polymer International*. 60 (10), 1548-1555.
- Zhang, Q., Shi, L., Nie, J., Wang, H. and Yang, D. (2012). Study on poly(lactic acid)/natural fibers composites. *Journal of Applied Polymer Science*. 125 (S2), 526-533.
- Zhang, C., Wang, W., Huang, Y., Pan, Y., Jiang, L., Dan, Y., Luo, Y. and Peng, Z. (2013). Thermal, mechanical and rheological properties of polylactide toughened by epoxidized natural rubber. *Materials and Design*. 45 198–205.
- Zhang, Z., Zhao, X., Wang, S., Zhang, J. and Zhang, W. (2014). Inducing a network structure of rubber phase: an effective approach to toughen polymer without sacrificing stiffness. *RSC Advances*. 4 (105), 60617-60625.
- Zhao, Q., Ding, Y., Yang, B., Ning, N., Fu, Q. (2013) Highly Efficient Toughening Effect of Ultrafine Full-Vulcanized Powdered Rubber on Poly(lactic Acid) (PLA). *Polymer Testing*. 32 (2), 299-305